

## DIRECT FLOOR COVERINGS LOOSELAY SPECIFICATIONS

### Dimensional Stability EN 434Pass

Total Thickness (mm)	EN 649	5.0mm
Thickness of wear layer (mm)	EN 428	0.7mm (+/- 0.005)
Peeling strength of layer (mm)	EN 431	Pass
Weight (+/- 50gr/m2)	EN 430	8.3kg/m2
Plank Dimension	EN 427	177.8mm x 1219.2mm
Packing	EN 427	10 Planks/2.167m2 per box
Sound, Impact reduction	EN ISO 717-2	> 5DB
Colour fastness to light	ISO 105 B02	Grade > 6
Static Indentation	EN 433	< 0.1mm

Flexibility	EN 435	Pass
Abrasion resistance	EN 660	Class T
Castor chair resistance	EN 425	Pass
Slip resistance	EN13893/DIN 51131	(> 0.3) R10
Fire rating	ASTM E 84, EN13501-1	Class 1, BFL – S1
Usage category	EN 685	23/42
Resistance to Chemical	EN423	Pass
Electrostatic properties	EN 1815	< 2kv
Surface treatment		PUR
Embossing	Regular/Deep/Wild	